



# Rebel



**Textaaf foam**  | Comfort  
creativity in fabrics



# Rebel

We introduce a new cord quality for Textaafoam. The name is Rebel and comes in a wide colour line. This upholstery fabric is part of our Comfort Collection, due to its softness and elegancy.

Our product development team decided that it was time for another new cord quality, especially now that the articles Ribcord and Bodega are still running very well. This season we see that cord is back in trend, therefor we are bringing this new cord quality.

Cord qualities are ideal for upholstery so Rebel will fit every type of furniture. Cord qualities are known for its striped (warp) patterning and the extra value its soft pile adds to the furniture.

Rebel is piece dyed and durable with Martindale of 100.000 rubs. Even washable (machine) at 30 degrees\*. Due to its broad colour line, you will find it easy to combine with many other Textaafoam Originals.

Did you know? Cord qualities are traditionally used in making British country clothing, even though its origin lies among items worn by townspeople in industrial areas. Although cord has existed for a long time and was used in Europe since the 18th century, only in the 20th century did it become global, notably expanding in popularity during the 1970s. Since then it comes and goes, but for us these kind of articles are performing well over the years.

The rib of this article is 5,3 mm and the base fabric in between 0,5 mm.

- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.

***Textaafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

## Composition

/ faceside 95%PES 5%NY  
/ backside 100%PES  
/ ribcord

## Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



anthracite 67



cabernet 205



carmine 36



cognac 28



copper 126



cream 02



emerald 184



forest 162



gold 132



grey 65



indigo 90




jungle 207

Please note: colours may vary according to your screen settings.





lightgrey 60



magnolia 160



onyx 169



pistachio 52



shell 196



shitake 124



steel 149



taupe 12



thyme 206



wenge 192

Please note: colours may vary according to your screen settings.

Rebel - Article passport

Rebel is a piece dyed article with a full and soft grip.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

|                      |                                                               |  |
|----------------------|---------------------------------------------------------------|--|
| Productgroup         | ribcord                                                       |  |
| Applications         | sofa's, beds, chairs with fitted and loose fitting upholstery |  |
| Composition faceside | 95%PES 5%NY                                                   |  |
| Composition backside | 100%PES                                                       |  |
| Bonding              | woven                                                         |  |
| Statistic code       | 54075200                                                      |  |
| Dyeing method        | piece dyed                                                    |  |
| Available colours    | 22                                                            |  |
| Packaging            | bubble wrap                                                   |  |

Durability specifications

| Test                                | Test specification                                                                                                                                                                                                                    | Executed by laboratory: | Unit   | Testresult |     | Norm RAL GZ 430/4:2019-01 |                    | Norm DIN EN 14 465:2006-09 |
|-------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------|--------|------------|-----|---------------------------|--------------------|----------------------------|
|                                     |                                                                                                                                                                                                                                       |                         |        | Dry        | Wet | DGM                       | DGM+               |                            |
| Abrasion resistance - yarn breakage | DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03                                                                                                                                                                                | CTL                     | cycles | >100.000   |     | min. 20.000               | min. 40.000        | A                          |
| Pilling                             | DIN EN ISO 12945-2:2000-11. 2000 cycles                                                                                                                                                                                               | CTL                     | grade  | 4-5        |     | min. 3-4                  | min. 4             | A                          |
| Colour fastness to light            | DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5                                                                                                                                                                               |                         |        |            |     |                           |                    |                            |
|                                     | light colours                                                                                                                                                                                                                         | CTL                     | grade  | 4-5        |     | min. 4                    | min.5              | B-C                        |
|                                     | middle colours                                                                                                                                                                                                                        | CTL                     | grade  | 4-5        |     | min. 4                    | min.5              | B-C                        |
|                                     | dark colours                                                                                                                                                                                                                          | CTL                     | grade  | 4-5        |     | min. 4                    | min.5              | B-C                        |
| Colour fastness to rubbing          | DIN EN ISO 105-X12:2016-11                                                                                                                                                                                                            |                         |        |            |     |                           |                    |                            |
|                                     | light colours                                                                                                                                                                                                                         | CTL                     | grade  | 4-5        | 4-5 | dry: 4, wet: 3            | dry: > 4, wet: 3-4 | A/A                        |
|                                     | middle colours                                                                                                                                                                                                                        | CTL                     | grade  | 4-5        | 4-5 | dry: 4, wet: 3            | dry: > 4, wet: 3-4 | A/A                        |
|                                     | dark colours                                                                                                                                                                                                                          | CTL                     | grade  | 4-5        | 4   | dry: 4, wet: 3            | dry: > 4, wet: 3-4 | A/A                        |
| Ignitability (cigarette test)       |  BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette | CTL                     |        | passed     |     |                           |                    |                            |

Processing specifications

| Minimum workable width in centimeters     | ± 143                                  |                         |        |            |      |                           |          |                            |
|-------------------------------------------|----------------------------------------|-------------------------|--------|------------|------|---------------------------|----------|----------------------------|
| Roll length in meters                     | ± 45                                   |                         |        |            |      |                           |          |                            |
| Material weight in grams per linear meter | ± 490                                  |                         |        |            |      |                           |          |                            |
| Test                                      | Test specification                     | Executed by laboratory: | Unit   | Testresult |      | Norm RAL GZ 430/4:2019-01 |          | Norm DIN EN 14 465:2006-09 |
|                                           |                                        |                         |        | Warp       | Weft | DGM                       | DGM+     |                            |
| Tensile strength                          | DIN EN ISO 13934-1:2013-08             | CTL                     | Newton | 942        | 728  | min. 350                  | min. 400 | A/A                        |
| Tear growth resistance                    | DIN EN ISO 13937-3:2000-06             | CTL                     | Newton | 73,1       | 40,6 | min. 25                   | min. 30  | A/A                        |
| Resistance to seam slippage               | DIN EN ISO 13936-2:2004-07. Load 180 N | CTL                     | mm     | 2,5        | 3,0  | max. 5                    | max. 4   | A/A                        |
| Delamination                              | DIN 53530:1981-02                      | CTL                     | Newton | 24,6       | 27,5 | n/a                       | n/a      | n/a                        |
| Chemical substances                       | REACH                                  | Centexbel               |        | passed     |      |                           |          |                            |
|                                           | Oeko-Tex, product class II             | Centexbel               |        | certified  |      |                           |          |                            |

Cleaning specifications

| Test                                                           | Test specification                                                        | Executed by laboratory: | Unit | Testresult |      | Norm RAL GZ 430/4:2019-01 |      | Norm DIN EN 14 465:2006-09 |
|----------------------------------------------------------------|---------------------------------------------------------------------------|-------------------------|------|------------|------|---------------------------|------|----------------------------|
|                                                                |                                                                           |                         |      | Warp       | Weft | DGM                       | DGM+ |                            |
| Dimensional change for washing 30 degrees celcius / air drying | DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08 | CTL                     | %    | 0,0        | 0,0  | n/a                       | n/a  | A/A                        |



- Dirt and damp prevention treatment applied.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.



Textaafoam  
creativity in fabrics

Textaafoam b.v.

La Défense 11 | 5026 SC Tilburg  
P.O. Box 12 | 5050 AA Goirle  
The Netherlands

T +31(0)13 534 5934

F +31(0)13 534 7586

E info@textaafoam.nl

www.textaafoam.nl

nov 2025