

Ribcord



















Ribcord

Meet our Ribcord, a Textaafoam evergreen. This soft corduroy is available in a wide, modern and trendy colour line. Suitable for all types of upholstery and in our Comfort Collection. Why? Because of its softness, volume and elegance.

This cord is successful for several years, so our product development team, decided that it was time for some new trendy colours. Bodega and Rebel are also running well cord textiles and in 2022 these kind of qualities are in trend.

Ribcord is produced in a very cool way, initially it is woven as a flatweave, formed by warp and weft yarns which are crossing at right angles to each other. Loops are woven in this textile and in the production process these loops are actually cut open and shaved to obtain an equal height. Corduroys can be produced in different widths, ours is rather wide and is piece dyed.

This upholstery textile is durable (over 100.000 rubs) and kindly note that the cord is in the warp (length) direction of the roll. Try to upholster on tight or loose fitted furniture, the result will be a nice, soft and luxurious look & feel. Machine-washable at 30 degrees, so when there are loose covers, perfect to clean and maintain.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Textaafoam originals Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.

Composition

/ faceside 88%PES 12%PA / backside 100%PES / ribcord

Suitable for



Please note: colours may vary according to your screen settings.



Please note: colours may vary according to your screen settings.



Please note: colours may vary according to your screen settings.







turtle 88

wenge 192 (new colour)

white 104



winered 39

Ribcord - Article passport

Meet our Ribcord, a Textaafoam evergreen. This soft corduroy is available in a wide, modern and trendy colour line. Suitable for all types of upholstery and in our Comfort Collection. Why? Because of its softness, volume and elegance.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics		
Productgroup	ribcord	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	88%PES 12%PA	
Composition backside	100%PES	
Bonding	woven	
Statistic code	54076130	
Dyeing method	piece dyed	
Available colours	40	
Packaging	transparent plastic	

Durability specifications			_	1		1				
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09		
				Dry	Wet	DGM	DGM+			
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	100.000		min. 20.000	min. 40.000	А		
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	А		
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5									
	light colours	CTL	grade	5		min. 4	min.5	В		
	middle colours	CTL	grade	5		min. 4	min.5	В		
	dark colours	CTL	grade	5		min. 4	min.5	В		
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11	DIN EN ISO 105-X12:2016-11								
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A		
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A		
	dark colours	CTL	grade	4-5	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A		
gnitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette		CTL		passed					

Processing specifications								
Minimum workable width in centimeters	± 140							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 540							
Test	Test specification	Executed by laboratory:	Unit	Test	result	Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.432	973	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	96,4	70,4	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	1,8	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	15.4	32.5	n/a	n/a	n/a

Cleaning specifications								
Test	Test specification	Executed by Unit Testresult laboratory:	result	Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09		
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,8	0,0	n/a	n/a	A/A

Centexbe

Centexbel



Chemical substances









REACH

Oeko-Tex, product class II







passed

certified













creativity in fabrics

Textaafoam b.v.La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934 F +31(0)13 534 7586 E info@textaafoam.nl www.textaafoam.nl