



Piquet





Piquet

This elegant upholstery textile is in the Textaafoam Natura Collection. A collection that stands for luxurious and natural fabrics.

This luxurious flatwoven fabric is one of Textaafoam originals, developed with a creative European weaver, who is known for its natural and authentic upholstery textiles.

Piquet is piece dyed, woven on a dolby-loom and the combination of natural and synthetic yarns, makes it an exclusive, luxurious and strong textile suitable for many different types of upholstery.

Loose or tight fitting upholstery, it always gives the sofa, chair or bed an enormous added value, to its special look & feel. This textile is available in a wide, soft and timeless colour line, washable at 30 degrees machine-wash.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

***Textaafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 40%VI 22%PES 20%CO 18%LI
/ backside n/a
/ flatweave

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery



anthracite 67




ashgrey 40



aubergine 74



beige 05




bisque 91



blossom 166



brown 15



chocolate 17



clay 84



coffee 81



darkbeige 08



darkbrown 18

Please note: colours may vary according to your screen settings.




desert 109



dolphin 180




ecru 102



espresso 123



graphite 66



grey 65



khaki 51



lightgrey 60



linen 110



liver 10



mint 50




natural 01

Please note: colours may vary according to your screen settings.



ocre 23



plumb 168



sand 03



sky 142



stone 181



tobacco 111



vanilla 04



wood 108

Please note: colours may vary according to your screen settings.

Piquet - Article passport

A luxurious flatwoven fabric with a combination of natural and synthetic yarns.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	40%VI 22%PES 20%CO 18%LI	
Composition backside	n/a	
Bonding / Coating	n/a	
Statistic code	55169300	
Dyeing method	yarn dyed	
Available colours	34	
Packaging	transparent plastic	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	28.000		min. 12.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	4-5		min. 4	min.5	B-C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	3	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/B
	dark colours	CTL	grade	4-5	2-3	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/C
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 25							
Material weight in grams per linear meter	± 588							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.500	710	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	49,0	54,0	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	3,3	3,8	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	1,0	1,5	n/a	n/a	A/A
 - We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.								



Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl