Varese



Textaafoam | Comfort
Expect what's next in furniture fabrics

Varese

Varese is an upholstery textile in the Textaafoam Comfort Collection, a range of soft and elegant upholstery fabrics.

Inspired by the layered landscape of Varese, this expressive bouclé offers a voluminous look with a luxurious high-low effect. The jacquard woven construction creates a soft handfeel and a lively, tactile surface.

The use of multicoloured and tonal yarns creates depth and variation across the fabric, highlighting the richness of its bouclé texture. The warm, timeless palette ensures versatility, making Varese an elegant choice for both modern and classic interiors.

This high-quality upholstery textile is suitable for all types of furniture: fitted, buttoned and loose fitting.

- Always be careful with sharp or rough objects such as watches, buckles, or velcro, as they may damage the fabric.

- When a loop does occur, it can be easily pushed back into the fabric with a blunt object.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Textaafoam originals *Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 72%PES 18%PAC 10%RPP
/ backside n/a
/ jacquard

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery



beige 05



desert 109



forest 162



linen 110



shell 196



shitake 124

Please note: colours may vary according to your screen settings.

Varese - Article passport

An expressive bouclé article with a voluminous look and a luxurious high-low effect.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	jacquard	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	72%PES 18%PAC 10%RPP	
Composition backside	n/a	
Bonding / Coating	n/a	
Statistic code	58013600	
Dyeing method	yarn dyed	
Available colours	6	
Packaging	transparent plastic	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	55.000		min. 16.000	min. 25.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test) 	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138
Roll length in meters	± 25
Material weight in grams per linear meter	± 856

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	2.204	838	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	314,0	400,0	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,7	2,8	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-1,0	-1,0	n/a	n/a	A/A
	- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.							

Textaafoam
Expect what's next in furniture fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl

okt 2026