

Facet - Article passport

Woolly fabric with a soft grip. Made from recycled material.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery, drapery
Composition faceside	75%WO 25%PA
Statistic Code	51113080
Dyeing method	yarn dyed
Available colours	40

Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100,000		min. 12.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	3-4		min. 3-4	min. 4	C
Colour fastness to light	DIN EN ISO 105-B02:2014-11, Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min. 5	B
	middle colours	CTL	grade	5		min. 4	min. 5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324, Schedule 4 part I, Ignition source 0: cigarette		Centexbel		passed			
	DIN EN ISO 1021-1:2014, Source: Smouldering cigarette		Centexbel		passed			
Ignitability (match test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324, Schedule 4 part I, Ignition source 1: Match flame equivalent		Centexbel		passed			
	DIN EN ISO 1021-2:2014, Source: Match flame equivalent		Centexbel		passed			

Processing specifications

Minimum workable width in centimeters	± 145							
Roll length in meters	± 50							
Material weight in grams per linear meter	± 600							
Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	455	348	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	40,5	35,2	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180 N	CTL	mm	2,7	2,7	max. 5	max. 4	A/A
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl